

Arcrete CN

Corrosion Inhibitor Concrete Admixture

DESCRIPTION

Arcrete CN is supplied ready for use. It should be added to concrete mixes either during the mixing cycle or at the same time as the water, or alternatively it should be added in its supplied form to a normal concrete mix a few minutes before the pour is made. In the latter case further mixing should be provided to ensure complete dispersion.

TYPICAL PROPERTIES

Appearance: Yellowish Clear Liquid

Specific Gravity: 1.14 at 25°C

Chloride Content: Nil as per BS 5075

COMPATIBILITY

With Cements:

Arcrete CN is compatible with all Portland, Pozzolanic and blast furnace cements (GGBFS) as It is also compatible with concrete containing fly ash and silica fume.

With Other Admixtures:

Arcrete CN is compatible with other ARKAZ admixtures in the same concrete mix. All admixtures should be added to the concrete separately and must not be mixed prior to addition. The performance of concrete containing more than one admixture should be assessed by trial mixes to ensure the desired combination of effects is obtained.

ADDITION RATES

Range:

Typical specified dosage levels are normally in the range of 12 to 30 liters per cubic meter of concrete. Because **Arcrete CN** has a high dosage level, calculation of water cement ratio should include the water added to the mix in the admixture.

The optimum dosage is assessed after preliminary trials depending upon the actual mix constituents and specifications required.

Addition rates outside of the recommended dosage range may be used for special concrete applications. In such circumstances it is important to conduct preliminary trials on the actual mix constituents to assess the effect on the properties of the concrete at the dosage level specified.

DISPENSING

It is preferable that **Arcrete CN** should be introduced into the mixer by means of independent automatic dispensing equipment. Such equipment or advice on dispensing can be obtained from Arkaz.

METHOD OF USE

Arcrete CN is supplied ready for use. It should be added to concrete mixes either during the mixing cycle or at the same time as the water, or alternatively it should be added in its supplied form to a normal concrete mix a few minutes before the pour is made. In the latter case further mixing should be provided to ensure complete dispersion.

PACKAGING

Arcrete CN is supplied in 210 non-returnable drums. Alternatively, 1,000 liter totes and bulk deliveries can be arranged.

HEALTH AND SAFETY

For more Safety information you can check Product Material Safety Data Sheet, send an email to ConcreteDoctor@arkaz.com or Contact Arkaz Technical Department.

STORAGE & SHELF LIFE

Arcrete CN should be stored in original containers or suitable closed tanks preferably away from extreme temperature. Always keep product in shaded storage.

Storage Life: 12 months from date of manufacture.

TECHNICAL SERVICE

The technical service department of Arkaz is available to assist in the correct and best use of our products, these resources and advice are at your disposal entirely without obligation.

Please contact:
concretedoctor@arkaz.com

LEGAL DISCLAIMER

The information given is based on data and knowledge considered to be true and accurate and is offered for the user's consideration, investigation and verification. Since the conditions of use are beyond our control, we do not warrant the results to be obtained. Please read all statements, recommendations or suggestions in conjunction with our conditions of sale including those limiting warranties and remedies which apply to all goods supplied by us. No statement, recommendation or suggestion is intended for any use which would violate or infringe statutory obligations or any rights belonging to a third party.

These products may be covered by patents or patents pending.



Copyright 2021
Printed in K.S.A. Version 2.0
21-March-2021