

PROTECTA® FR ACRYLIC

TECHNICAL DATA SHEET



General Product Description

Designed to prevent the spread of fire and smoke through joints and openings in fire rated walls and floors (including openings formed around building service penetrations); Protecta® FR Acrylic will also maintain acoustic design performance.

When subjected to atmospheric conditions, the sealant cures however, it will retain a degree of elasticity for joint movement. Under fire exposure, Protecta® FR Acrylic creates a robust fire seal by the formation of a durable intumescent char.

Protecta® FR Acrylic can be used with a suitable filling material i.e. stone wool or Protecta® backing material in order to secure correct width to depth ratio, and to reduce the shrinking of the sealant during curing. Minimum depth and maximum width of the joints are included in the installation instructions. Thermal activation takes place at approx. 180°C when the material will expand (intumesce) and prevent the passage of fire and smoke for periods up to and beyond 4 hours.

Properties

- High end formula, certified in most countries Worldwide
- Faster application times and minimal material use due to its ability to achieve high fire ratings and single sided installations
- Classified for fire sealing all types of constructions such as drywalls, masonry walls, concrete walls, concrete floors and composite floors
- Classified for fire stopping of service penetrations in cross-laminated timber walls and floors
- Classified for fire sealing all types of building service penetrations such as cables, cable bundles, cable conduits, steel pipes, copper pipes, composite pipes, PVC pipes, PE pipes, ABS pipes, PP pipes and PEX pipe-in-pipes
- Classified with commonly used pipe insulations such as stone wool, glass wool, elastomeric and phenolic, both interrupted and continuous through the fire seal
- Classified for fire sealing against timber, steel and aluminium such as door and window frames
- Causes no deleterious effects on cPVC pipes like BlazeMaster, supported by mechanical testing evidence
- May be installed in drywalls with or without framing around the opening
- Very high sound insulation
- Air, smoke and gas tight, tested at 600 Pascal
- Available in the Polyseam Eco-Foil system
- Low emissions - environmentally and user friendly
- Simple to apply with a smooth surface finish
- No priming necessary for application to most materials
- Suitable for most surfaces, including concrete, masonry, steel, gypsum, glass, plastics and most non-porous surfaces
- Hardens quickly and tack free after 1 hour (the fire performance specification of the joint filler has been derived when the joint filler has been let to cure for a month)
- 18 months storage time (under correct conditions)
- 30 years working life



Emission Data (indoor air quality)

Compound	Emission rate after 3 days	Emission rate after 4 weeks
TVOC	170 µg/m³	< 5 µg/m³
TSVOC	n.d.	< 5 µg/m³
VOC w/o NIK	25 µg/m³	< 5 µg/m³
R Value	0.33	0
Formaldehyde	< 3 µg/m³	< 3 µg/m³
Acetaldehyde	< 3 µg/m³	< 3 µg/m³
Sum for+ace	< 0.002 ppm	< 0.002 ppm
Carcinogenic	< 1 µg/m³	< 1 µg/m³
n.d. or < means not detected		

Regulation or Protocol	Conclusion
French VOC Regulation	A+
French CMR components	Pass
Italian CAM	Pass
ABG / AgBB to the guidelines of DIBt	Pass
Belgian Regulation	Pass
EMICODE	EC 1 PLUS
Indoor Air Comfort GOLD®	Pass
Blue Angel (DE-UZ 123)	Pass
BREEAM-International	Exemplary Level
BREEAM-NOR	Pass
LEED v4.1	Compliant

Protecta® FR Acrylic has been tested by Eurofins Product Testing; reports available upon request.

PROTECTA® FR ACRYLIC

TECHNICAL DATA SHEET



Sound Insulation

Description	Sound reduction
Single sided seal ≥12mm depth	Rw 62 dB
Double sided seal ≥12mm depth	Rw >62 dB

Protecta® FR Acrylic - tested at EXOVA BM Trada (UKAS accredited); according to EN ISO 10140-2:2010. Usage of any backing material is optional, due to the tests being conducted with sealant only.

Pipe End Configurations

When testing pipes, one can choose not to cap (or close) the pipe, or cap the pipe inside the furnace, or outside the furnace, or on both sides. The configuration chosen depends on the intended application of the pipe and/or the installation environment.

The code defining if a pipe is capped is stated after the fire classification. For instance, EI 60 C/U which means the pipe was capped inside the furnace, and uncapped outside the furnace. The test configuration defines the approvals possible.

Our engineering judgment based on EN 1366-3:2009 are:

Intended use of pipe		Pipe end condition ⁴⁾
Rainwater pipe, plastic	At drainage	U/U ¹⁾
	Not at drainage	C/C ²⁾
Drainage or sewage pipe, plastic	Ventilated drain	U/U ¹⁾
	Unventilated drain	U/C ¹⁾
	Drain w/water trap	U/C ¹⁾
	Not at drainage	C/C ²⁾
Pipe in closed circuit (water, gas, air, electricity etc.)		C/C ^{2) 3)}
Flue gas recovery system pipe, plastic		U/C ¹⁾
Pipe with open ends and ≥ 50cm length on both sides, plastic		U/U ²⁾
Pipe supported by suspension system, metal	Fire rated support	C/U ¹⁾
	Non-fire rated	U/C ¹⁾
Waste disposal shaft pipe, metal		U/C ¹⁾

¹⁾ Suggested in EN 1366-3:2009. ²⁾ Polyseam's judgment based on tests.

³⁾ Metal pipes should have fire rated support. ⁴⁾ U/U classified fire seals cover C/U, U/C and C/C. C/U classified fire seals cover U/C and C/C. U/C classified fire seals cover C/C.

Analysis of cPVC Pipes e.g. BlazeMaster

Analysed using Fourier Transform Infrared (FTIR) Spectroscopy; examination of the sealant contact regions of the cPVC pipe after removal of the sealant showed no evidence of visible discolouration or changes at the pipe surface.

Protecta® FR Acrylic has also been tested for chemical resistance of a sealant when applied to a cPVC pipe. The sealant does not affect cPVC pipes; the tests showed no difference between the control and exposed results at Yield.

Tested by Intertek, report numbers IWTN/W000009628ARL001 and WTN/W000009628RLM001.

Air Permeability

Positive Pressure (Pa)	Leakage (m³/h/m²)	Negative Pressure (Pa)	Leakage (m³/h/m²)
25	0.00	25	0.00
50	0.00	50	0.00
100	0.00	100	0.00
200	0.00	200	0.00
300	0.00	300	0.56
450	1.11	450	1.67
600	6.94	600	6.11

Protecta® FR Acrylic - tested at Warringtonfire Testing and Certification Ltd (UKAS accredited); according to EN 1026: 2016.

Technical Data

Condition	Ready for use, acrylic based filler
Specific gravity	1.56 – 1.60
Flash point	None
Reaction to fire	Class B-s1, d0
Air permeability	Air, smoke and gas tight tested to EN 1026: 2016
Expansion in fire	1 : 2-3
Non-sticky	Max. 75 minutes
Film forming	Max. 25 minutes
Totally hardened	3 to 5 days depending on thickness and temperature
Flexibility	12.5% according to ISO 11600
Durability	Z ₂ intended for use in internal conditions with humidity classes other than Z ₁ , excluding temperatures below 0 °C
BWR 3	Use category IA1, S/W3
Thermal conduct.	0.845 W/mK (+/- 3%) @ 20mm depth
Storage	18 months stored in unopened cartridges. To be stored in temperatures between 10 °C and 30 °C
Working life	30 years
Service temp.	-20 to +70 °C
Application temp.	+5 to +30 °C
Compatibility	Suitable for use with most materials, but should not be used in direct contact with bituminous materials
Limitations	Should not be used in permanently damp areas or in joints with high movement
Classification	CE-marked - Sealant for fire rated joints and penetrations class EI 240
Standard colours	Standard white, pure white, grey or red. Different batches may have minor colour deviations.
Colour codes	White: RAL 9002 / NCS S1002-Y Grey: NCS S5500-N
Packaging	Box containing 25 foils/cartridges each 300/310 ml Box containing 12 foil packed each 600 ml Pallets 310 ml: 64 boxes per pallet equals 1600 pcs Pallets 600 ml: 91 boxes per pallet equals 1092 pcs

Test Standards

This Technical Data Sheet and the Installation Instructions are based on the product's European Technical Assessment issued in accordance with regulation (EU) No 305/2011 on the basis of EAD 350454-00-1104, September 2017.