

Arcrete DP7

Concrete Plasticizer for Ready Mix Concrete
Comply to ASTM C494 Type A, B & D and BS EN 934-2

DESCRIPTION

Arcrete DP7 is a concrete plasticizer with set retardation effect developed to boost and improve the slump retaining properties of concrete, whilst providing improved compressive strengths, also it improves the workability of concrete as it is highly flexible and effective over a wide range of cement contents and types. The product is especially beneficial in hot climate conditions and complies to ASTM C494 and BS 934-2.

TYPICAL PROPERTIES

Appearance: Brown Liquid
Specific Gravity: 1.035 at 25 ± 1°C.
Chloride Content: Nil, according to BS 5075

COMPATIBILITY

With Cements:

Arcrete DP7 can be used with most types of Portland cements as well as Pozzolanic Cements, Ground Granulated Blast Furnace Slag (GGBFS), Micro Silica and Fly Ash

With Other Admixtures:

Arcrete DP7 performance will be affected by the presence of other chemical admixtures. We recommend Arkaz Technical Department to be contacted for Advice in these circumstances

ADDITION RATES

Average Addition Range:

0.1 % - 0.8 % (v/w) by wt. of cement

The optimum dosage is assessed after preliminary trials depending upon the actual mix constituents and specifications required.

Addition rates outside of the above dosage range may be used for special concrete applications. In such circumstances, it is important to conduct preliminary trials on the actual mix constituents to assess the effect on the properties of the concrete at the dosage level specified.

EFFECTS OF OVERDOSING

Serious overdosing of **Arcrete DP7** will generally produce a concrete mix of even greater workability, set retardation and a slight increase in air entrainment may be noticed. In SRC mixes and in cooler weather, set retardation will be further increased. If intentional or accidental increased above the recommended addition rates are encountered, care must be taken to allow for the effect on the stripping time of formwork. In such cases, however, provided the concrete is properly cured the ultimate strength will generally be higher than for normal concrete.

DISPENSING

It is preferable that **Arcrete DP7** should be introduced into the mixer by means of independent automatic dispensing equipment. Such equipment or advice on dispensing can be obtained from Arkaz.

METHOD OF USE

Arcrete DP7 is supplied ready for use. It should be added to concrete mixes either during the mixing cycle or at the same time as the water, or alternatively it should be added in its supplied form to a normal concrete mix a few minutes before the pour is made. In the latter case, further mixing should be provided to ensure complete dispersion.

PACKAGING

Arcrete DP7 is supplied in 210 non-returnable drums. Alternatively, 1,000-liter totes and bulk deliveries can be arranged.

HEALTH AND SAFETY

For further health and safety information, Check Product Material Safety Data Sheet , drop an email to Arkaz Concrete Doctor at ConcreteDoctor@arkaz.com or please consult Arkaz Technical Department.

STORAGE & SHELF LIFE

Arcrete DP7 should be stored in original containers or suitable closed tanks preferably away from extremes of temperature. The product should always be kept in shaded storage.

Storage Life in Manufacturer's Drums:
12 months from date of manufacture.

Storage Life in Bulk Storage:
12 months from date of delivery.

TECHNICAL SERVICE

The technical service department of Arkaz is available to assist in the correct and best use of our products, these resources and advice are at your disposal entirely without obligation.

Please contact:
concretedoctor@arkaz.com

LEGAL DISCLAIMER

The information given is based on data and knowledge considered to be true and accurate and is offered for the user's consideration, investigation and verification. Since the conditions of use are beyond our control, we do not warrant the results to be obtained. Please read all statements, recommendations or suggestions in conjunction with our conditions of sale including those limiting warranties and remedies which apply to all goods supplied by us. No statement, recommendation or suggestion is intended for any use which would violate or infringe statutory obligations or any rights belonging to a third party.

These products may be covered by patents or patents pending.



Copyright 2021
Printed in K.S.A. Version 2.0
3-March-2021