

ENEBOND SBR50



Styrene Butadiene Rubber (SBR) hydrolysis-resistant mortar modifier & bonding agent

DESCRIPTION

ENEBOND SBR50 is a blend of Styrene Butadiene Rubber, fine particle size, high performance cement-based compositions modifying agent. It is formulated to improve workability & flow properties and reduce W/C ratio enabling more improvement of physical and mechanical properties. It has an excellent adhesion to aged concrete. It resists the hydrolysis after hardening and can be used for external & internal applications, it can be used also as a primer for the aged and freshly laid concrete.

USAGES

- As an old-new concrete bonding agent along with concrete repair compounds
- As an adhesive for a wide range of substrates, including concrete masonry brick, glass, and metal wood
- Used as curing compound
- Concrete repairs & floor patching where a highly flowable replacement materials and heavy-duty screed mortar is required

ADVANTAGES

- Excellent adhesion
- Improved chemical and abrasion resistance
- Improved crack bridging of concrete
- Improved durability
- Improved protection against carbonation of concrete
- It does not re-emulsify in the presence of water and in alkaline medium
- Reduced W/C ratio and improved workability
- Water-based, non-flammable, non-toxic, and non-corrosive

TECHNICAL DATA

ENEBOND SBR50

Typical values

<i>Appearance</i>	White liquid
<i>Specific gravity</i>	1.01 ± 0.05
<i>pH value</i>	7 – 8
<i>Shrinkage during cure</i>	0.02 %
<i>Compressive strength</i>	30 N/mm ² (control) 35 N/mm ² (result)
<i>Tensile strength</i>	4.5 N/mm ² (control) 9.5 N/mm ² (result)

STANDARDS

ENEBOND SBR50 is formulated to comply with;

- ANSI A 118.4 & ANSI A136.1
- ASTM C-631 & ASTM C-932 Bonding compound- exterior use

USAGE INSTRUCTIONS

1. Surface preparation

All surfaces shall be sound, clean and free from dust, oil & grease or any contaminants that may affect the bond between the product and substrate. Metal surfaces shall be free from rust & scale and other contaminants. Absorbent surfaces shall be saturated thoroughly.

2. Mixing

Dilute **ENEBOND SBR50** with water by mixing before adding to any dry mix.

3. Application

For screed & topping application:

- Mix 1-2 liter of **ENEBOND SBR50** with 3 kg of Portland cement and apply it on a cleaned surface using brush before 15 minutes of screed application.
- For concrete repair exceeding 10 cm, follow screed procedures as mentioned above.
- For mixing with dry mix materials follow the instruction as mentioned in method statement.

4. Cleaning

ENEBOND SBR50 to be cleaned from tools and equipment after finishing work immediately by splashing water.

PACKAGING

ENEBOND SBR50 is supplied in 20 liters or 200 liters pail.

HEALTH & SAFETY

ENEBOND SBR50 is non-toxic and non-hazardous, if any materials come in contact with skin; cleaning with water and soap is recommended.

STORAGE & SHELF LIFE

ENEBOND SBR50 shall be stored in normal conditions away from any extreme temperatures.
Shelf life is 12 months.

TECHNICAL SERVICE

The technical service department of Arkaz is available to assist in the correct and best use of our products, these resources and advice are at your disposal entirely without obligation. Please contact us via our website arkaz.com

LEGAL DISCLAIMER

The information given is based on data and knowledge considered to be true and accurate and is offered for the user's consideration and verification. Since the conditions of use are beyond our control, we do not warrant the results to be obtained. Please read all statements, recommendations or suggestions in conjunction with our conditions of sale including those limiting warranties and remedies which apply to all goods supplied by us. No statement, recommendation or suggestion is intended for any use which would violate or infringe statutory obligations or any rights belonging to a third party.

These products may be covered by patents or patents pending.