

PIOREP CF

High performance extra fine premixed crack filler

DESCRIPTION

PIOREP CF is high performance, non-oxidized, non-shrink single component crack filler, that contains blended cements, graded sand & chemical additives to improve consistency, surface finish and workability, it can be used to fill cracks, honeycomb, and cosmetic finish over minor defacements.

USAGES

- Crack filler to be used over smooth concrete and plastered surfaces, and it can be used for cracks upto 5 mm thickness
- Repair interior and exterior façade onto wet and dry walls & ceilings.

ī.

TECHNICAL DATA

PIOREP CF	Typical values
Appearance	White/ Grey powder
Grain size	≤ 0.075 mm
Bulk Density	1.0±0.1 kg/l
Wet Density	1.85±0.1 kg/l
Thickness range	Up to 5mm
Pot Life	20 – 45 min
Setting Time	60 min
Compressive strength	≥ 15 N/mm²
Flexural strength	≥ 2 N/mm²

CONSUMPTION

PIOREP CF

Water/20 kg	5.75 – 6.25 liters
Water/50 kg	16 – 18 liters
Yield/50kg bag	27 liters

STANDARDS

PIOREP CF complies with;

- ASTM C109
- ASTM C348
- ASTM C150
- BS EN 1015-12

ADVANTAGES

- Requires only addition of water on site at application time
- Adjustable consistency
- High mechanical & heat resistance properties
- Low permeability ensuring durability
- Non-toxic and does not contain any harmful ingredient
- High early and ultimate strengths
- Compatible with concrete surfaces
- Formulated for the Middle East climate

USAGE INSTRUCTIONS

1. Surface preparation

All surfaces shall be sound, clean and free from dust, oil & grease and any contaminants that may affect the bond between the product and substrates. It is recommended to open cracks and clean them by air blower and surface should be wetted by water reaching SSD (Saturated Surface Dry) condition prior to applying.

2. Mixing

Use a suitable clean container, add suitable amount of water per bag (refer to the table), and add **PIOREP CF** gradually, mixing simultaneously using high torque medium speed drill mixer of speed 400-500 rpm and a proper paddle for about 60 seconds, mix thoroughly until homogeneity is achieved.



3. Application

After thoroughly mixing **PIOREP CF** with water, apply it on the moistened wall surface firmly from bottom to upward direction uniformly with the help of putty blade scrapper. This would ensure less wastage and proper finish.

4. Curing

PIOREP CF is a cement-based material, that should be cured properly by spraying water for 3 days.

5. Cleaning

Tools contaminated with **PIOREP CF** may be cleaned using clean water, hard material can be removed by hand tools or mechanically.

PACKAGING

PIOREP CF is supplied in 20kg & 50kg bags.

HEALTH & SAFETY

PIOREP CF is non-toxic and non-hazardous if material comes in contact with skin, cleaning with water and soap is recommended.

For Ecology: Do not dispose directly to water or soil, re-use it if possible or mix with water and wait until it hardens then bury it in landfill in accordance with national regulation.

STORAGE & SHELF LIFE

PIOREP CF shall be stored in normal conditions away from extreme temperatures, and any source of moisture. Shelf life is 12 months.

TECHNICAL SERVICE

The technical service department of Arkaz is available to assist in the correct and best use of our products, these resources and advice are at your disposal entirely without obligation. Please contact:

concretedoctor@arkaz.com

LEGAL DISCLAIMER

The information given is based on data and knowledge considered to be true and accurate and is offered for the user's consideration, investigation and verification. Since the conditions of use are beyond our control, we do not warrant the results to be obtained. Please read all statements, recommendations or suggestions in conjunction with our conditions of sale including those limiting warranties and remedies which apply to all goods supplied by us. No statement, recommendation or suggestions in intended for any use which would violate or infringe statutory obligations or any rights belonging to a third party.

These products may be covered by patents or patents pending.



Copyright 2021 Printed in K.S.A. Version 2.0 13-March-2020