

## QUICKSEAL

## PP 350

### DESCRIPTION

**QuickSeal PP 350** is a spray applied, instant curing flexible membrane that can be built to any thickness in one application.

**QuickSeal PP 350** sits at the top of our QuickSeal range of waterproofing and containment membranes. Due to its unique chemistry it can be applied in virtually any environmental conditions. Very cold, very hot or even very humid environments will not negatively impact on the curing time or physical performance of QuickSeal PP 350.

**QuickSeal PP 350** provides a flexible, seamless, hard wearing substrate protection solution for a wide range of substrates. Its rapid spray application and instant curing characteristics enable shorter shut down times than traditional glue in place rubber membranes or fix in place jointed panel products.

**QuickSeal PP 350** is specially formulated and designed for different options of application techniques, which allows to apply this material by plural component hot spray high pressure or with cold spray low pressure machines like VIP's LP-2. So therefore the operator can select the adequate application technique for the specific job and project size.

### FEATURES

- Can be applied even under extreme climatic conditions. Hot, cold and humid conditions
- Good elongation at break.
- Good tensile strength.
- Seamless Waterproofing and liquid containment. No welding of joints – totally seamless. Seamless application and seamless finish. No welded joints or glued seams.
- Excellent adhesion to concrete, steel, aluminum, plastics, fibers, wood, foam etc.
- Can be applied across multiple substrates in the same application process.
- Remains flexible under a wide range of climatic conditions.
- Rapid application to any thickness and very fast cure results in faster turn around times. Can build to any thickness in one application. Does NOT require multiple coats.
- 100% solids, VOC-free, contains zero solvents

### TYPICAL USES

- Large scale Waterproofing for Commercial, Industrial & manufacturing facilities.
- Sealing and substrate protection. – Plant rooms, trafficable roof decks.
- Waterproofing and substrate protection for areas exposed to high wind abrasion.
- Waterproofing of water features, pools and ponds with high levels of residual substrate moisture. Under concrete screed waterproofing of large scale podium decks where residual moisture exists. Bridge, street and tunnel waterproofing particularly in high moisture environments.
- Lining of non-potable water tanks, waste water tanks.
- Loading docks and access ramps.
- For all waterproofing containment applications where there are no aggressive chemicals and or abrasive forces. For aggressive chemicals and / or high abrasion and impact loads please refer to our QuickSpray Industrial and QuickSpray Supreme range of products.

# QUICKSEAL

## PP 350

### PROCESSING PROPERTIES

### INFORMATION ABOUT THE USE OF THE PRODUCT

|  | DATA   |
|--|--|
| Mixing ratio of Comp. A to Comp. B                 | 1 : 1 by volume  |
| Material consumption [kg/m <sup>2</sup> /1mm]      | Approx. 1.0  |
| Recommended thickness [mm]                         | Minimum: 1.0 (on steel)<br>Minimum: 1.5 (on concrete)<br>Maximum: indefinite |
| Gel time at 25°C [sec.]                            | 5 - 10 (dependent on ambient and substrate temperature)                      |
| Tack Free-Time at 25°C [sec.]                      | 15 - 30 (dependent on ambient and substrate temperature)                     |
| Over coat cycle [h]                                | 0 – 10 Hours (without prep and priming)                                      |
| Curing/loading after [h]                           | Walkable: 1<br>Mechanical: 2<br>Chemical: 12-24                              |
| Temperature range for application (ambient) [°C]   | 0- +50   |
| Temperature range for application (substrate) [°C] |  |
| Material Temperature (Preconditioning) [°C]        | 25 - 30  |
| Material Temperature (Spraying) [°C]               | 70 – 80  |
| Maximal relative air humidity for application [%]  | 98   |
| Pay attention to the dew point limit               | min. 3K > DP (dew point)   |

**QUICKSEAL**
**PP 350**
**PHYSICAL PROPERTIES**
**INFORMATION ABOUT THE USE OF THE PRODUCT**

|                              | DATA                             |   |
|------------------------------|----------------------------------|---|
| Chemical Base                | –                                | Comp. A: MDI-Prepolymer<br>Comp. B: Polyetheramine-Mixture    |
| VOC-content                  | DIN EN ISO 11890-1 / ASTM D-1259 | 0%  |
| Solids content               | DIN EN 827 / ASTM D-2697         | 100%  |
| Color                        | –                                | Natural colour is a straw / brownish colour.<br>Un-pigmented. |
| Viscosity [mPa*s] @ 25° C    | DIN EN ISO 2884-2 / ASTM D-4878  | Comp. A: 300 – 1.000<br>Comp. B: 600 – 1.350                  |
| Density [g/cm³] @ 20° C      | DIN EN ISO 2811-2 / ASTM D-1217  | Comp. A: 1,09 – 1,13<br>Comp. B: 0,98 – 1,02                  |
| Density [g/cm³]              | EN ISO 1183 / ASTM D-792         | 1,02 ± 0,02   |
| Tensile strength [MPa]       | ISO 37 / ASTM D-638              | ≥ 17  |
| Modul [MPa]                  |                                  | 100% Elongation: ≥ 8<br>300% elongation: ≥ 13                 |
| Elongation at break [%]      |                                  | 300 – 350   |
| Hardness [Shore D]           | ISO 868 / ASTM D-2240            | 45 ± 5  |
| Rebound resilience [%]       | ISO 4662 / ASTM D-7121           | ≥ 32  |
| Tear growth resistance[N/mm] | ISO 34-1 method A                | ≥ 15  |
| Volume abrasion [mm³]        | DIN ISO 4649                     | ≤ 250   |

**QUICKSEAL**
**PP 350**
**PHYSICAL PROPERTIES**
**INFORMATION ABOUT THE USE OF THE PRODUCT**

|  | DATA                          |   |
|--|-------------------------------|---|
| Taber Abrasion [mg]                    | ASTM D-4060                   | < 8 (Wheel CS17 / 1.000g / 1000 Cycles)<br>< 80 (Wheel H18 / 1.000g / 1000 Cycles)              |
| Peel off strength [N/mm]               | ISO 813 / ASTM D-903          | Concrete: ≥ 4<br>Steel: ≥ 8   |
| Pull off strength [N/mm <sup>2</sup> ] | DIN EN ISO 4624 / ASTM D-4541 | Concrete: ≥ 1,5<br>Steel: ≥ 5   |
| Min. Process temp. [°C]                | ISO 11346 / ASTM D-2485       | - 40  |
| Max. Process temp. [°C]                |                               | Wet: 45<br>Dry: 90<br>Peak temperature dry: 120   |
| Heat Conductivity [W/m*K]              | -                             | 0,245   |
| Sound absorption                       | -                             | > 10 dB (A)   |
| Surface resistance [Ohm]               | DIN IEC 60167                 | ≥ 1,0*10 <sup>11</sup>  |
| Volume resistance [Ohm]                | DIN IEC 60093                 |   |
| Storage conditions [°C]                | DIN EN 12701                  | 10 – 30 (in closed original drums, stored at dry and well ventilated place; beware of freezing) |
| Shelf life                             | -                             | Approximately 12 months   |

## QUICKSEAL

## PP 350

### APPLICATION NOTES

The gel times and tack free times depend on the surrounding climatic conditions and the temperature of the substrate, e.g. ambient temperature, substrate temperature, relative humidity and ventilation etc.

Therefore the data specified above can only be used as a guide.

Aromatic Polyurea Coating Systems are UV-stable but are not colour stable. The cured coating system may exhibit discoloration when exposed to sunlight. **This does not influence the physical properties of the material.**

### FORM OF DELIVERY

**Please see our price list for respective packaging units.**

### DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, at the time of printing. However the accuracy, completeness and repeatability of said tests results are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and tests, to determine the suitability of the product / system for his own particular project and application. User assumes all risk and liability resulting from his use of this product / system. We do not suggest or guarantee that any hazards listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or incorrect use of the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and standard application procedures. Test performance results were obtained in a controlled environment and the manufacturer makes no claim that these tests or any other tests, accurately represent all environments.

### ISSUE DATE: MARCH 2020

This technical specification supersedes all previous data sheets.