

# Arcrete G150

Plasticizer for Hot Weather Concrete

## DESCRIPTION

**Arcrete G150** is a Mid to High-Range Water Reducer based on modified Lignosulfonate salts developed to enhance and improve the slump retaining properties of concrete, whilst providing improved compressive strengths, as it improves the flow and strength development of concrete as it is highly flexible and effective over a wide range of cement contents and types. The product is especially beneficial in hot climate conditions.

**Arcrete G150** Complies with ASTM C494 Type D & G and BS EN 934-2.

## TYPICAL PROPERTIES

**Appearance:** Dark Brown Liquid

**Specific Gravity:** 1.175 at 25°C

**Air Entrainment:** 1.0% Max from Control Mix.

**Chloride Content:** Nil according to BS5075.

## COMPATIBILITY

### With Cements:

**Arcrete G150** is compatible with all Portland, Pozzolanic and Blast Furnace cements. It is also compatible with concrete containing fly ash and silica fume.

### With Other Admixtures:

**Arcrete G150** should not be premixed under any circumstances with other admixtures. The performance of the product will be affected by the presence of other chemical admixtures. We recommend Arkaz be contacted for Advice in these circumstances.

## ADDITION RATES

### Range:

0.5%-1.5 % (v/w) by wt. of cement  
500 ml to 1500 ml per 100 Kg of cement

The optimum dosage is assessed after preliminary trials depending upon the actual mix constituents and specifications required.

Addition rates outside of the recommended dosage range may be used for special concrete applications. In such circumstances it is important to conduct preliminary trials on the actual mix constituents to assess the effect on the properties of the concrete at the dosage level specified.

## EFFECTS OF OVERDOSING

Serious overdosing of **Arcrete G150** will generally produce a concrete mix of even greater workability, set retardation and a slight increase in air entrainment may be noticed. In SRC mixes and in cooler weather, set retardation will be further increased. If Intentional or accidental increased above the recommended addition rates are encountered, care must be taken to allow for the effect on the stripping time of formwork. In such cases, however, provided the concrete is properly cured the ultimate strength will generally be higher than for normal concrete.

## DISPENSING

It is preferable that **Arcrete G150** should be introduced into the mixer by means of independent automatic dispensing equipment. Such equipment or advice on dispensing can be obtained from Arkaz.

## METHOD OF USE

**Arcrete G150** is supplied ready for use. It should be added to concrete mixes either during the mixing cycle or at the same time as the water, or alternatively, it should be added in its supplied form to a normal concrete mix a few minutes before the pour is made.

In the latter case further mixing should be provided to ensure complete dispersion.

## PACKAGING

**Arcrete G150** is supplied in 210 non-returnable drums. Alternatively, 1,000-liter totes and bulk deliveries can be arranged.

## HEALTH AND SAFETY

For more Safety information you can check Product Material Safety Data Sheet, send an email to [ConcreteDoctor@arkaz.com](mailto:ConcreteDoctor@arkaz.com) or Contact Arkaz Technical Department.

## STORAGE & SHELF LIFE

**Arcrete G150** should be stored in original containers or suitable closed tanks preferably away from extreme temperature. Always keep product in shaded storage.

Storage Life in Manufacturer's Drums: 12 months from date of manufacture.

Storage Life in Bulk Storage: 12 months from date of delivery.

---

### TECHNICAL SERVICE

The technical service department of Arkaz is available to assist in the correct and best use of our products, these resources and advice are at your disposal entirely without obligation.

Please contact:  
concretedoctor@arkaz.com

### LEGAL DISCLAIMER

The information given is based on data and knowledge considered to be true and accurate and is offered for the user's consideration, investigation and verification. Since the conditions of use are beyond our control, we do not warrant the results to be obtained. Please read all statements, recommendations or suggestions in conjunction with our conditions of sale including those limiting warranties and remedies which apply to all goods supplied by us. No statement, recommendation or suggestion is intended for any use which would violate or infringe statutory obligations or any rights belonging to a third party.

These products may be covered by patents or patents pending.



Copyright 2021  
Printed in K.S.A. Version 2.0  
23-March-2021